

sikkens

ALPHA ELEGANCE

Decorative water-based finish, cloudy effect, for internal walls



Semi-transparent water-based decorative finish for interiors with a cloudy effect

PRODUCT FEATURES

composition:	Based on acrylic binder in aqueous dispersion and very fine pigments
main properties	<ul style="list-style-type: none"> - Highly decorative cloudy effect - Easy to apply - High resistance to wet abrasion - Resistant to scratches and wear - Can be painted over with any water washable paint

PHYSICAL CHARACTERISTICS

viscosity:	Brookfield 1000 - 1500 cps at 20 ° C
volume level (density):	1.00 ± 0.05 kg / dm ³
H:	7 - 9
solid content:	28.5% by volume; 29.5% by touch
drying at 23 ° C / 65% RH:	dry weight: 1 - 2 hours
overlay:	After 4 - 6 hours
coloring:	Only with Akzo Nobel's Acomix tinting system using the N00 base. Also available in the ready mixed Mother of Pearl finish.
EU limit value for OV content:	Cat. A / I: 200 g / l (2010). This product contains a maximum of 100 g / l of VOC

physical alues according to EN 13300

brilliance:	G.3Opaque	≤ 10 OJ 85 °
dry film thickness:	AND ₁	<50µm
ranulometry:	S1 End	<300 µm
wet abrasion:	Class 1	<5 µm after 200 cycles

ODO OF EMPLOYMENT

methods of application:

Short-haired wool roller and synthetic sponge or synthetic cloth. Alternatively, a synthetic fur glove can also be used. The product should be spread with a short-haired roller with vertical bands and, when still wet, go over with circular movements with a sponge or a synthetic cloth to create the effect. The Mother of Pearl finish is applied exclusively with a short-haired wool roller; after having distributed the product evenly, direct all the rolls upwards, when still wet.

ilution:

Ready to use for all colors except the Mother of Pearl finish which can be diluted up to max. 50% by volume with water, depending on the desired aesthetic effect.

hex:

13 - 14 m2 / l per coat.

The yield may vary according to the roughness, porosity and absorption characteristics of the substrates and the application system adopted.

**environmental conditions
for application:**

Temperature: 5 - 30 ° C; Relative humidity: max 85%.

tools ulice:

With water immediately after use, if necessary add a small amount of detergent.

onservation:

In tightly closed packs, in a cool and dry place, away from frost and heat sources.

warnings:

ALPHA ELEGANCE must be applied on perfectly dry, cured and compact substrates. The roller application of ALPHA ELEGANCE MADREPERLA, if used undiluted, tends to modify in a more or less evident way the chromatic effect of the underlying finish. To mitigate this phenomenon it is possible to dilute the product up to a max. 50% by volume with water, depending on the color previously used. To clean painted surfaces, we recommend using soft sponges and water mixed with POLYFILLA PRO S600 detergent in the ratio of 5 L of water to 35 ml of detergent. Avoid using abrasive rags or cloths and detergents containing alcohol or solvents of any kind. The final color can be perceived in a slightly different way from the folder reference depending on the nature of the supports and the amount of material applied. Operations such as sanding, sandblasting, flame removal, etc., of old paint layers, can generate dangerous dust and / or fumes. Work in well-ventilated areas and necessarily wear suitable personal protective equipment. For more information on the correct disposal, storage and handling of the product, please consult the relevant Safety Data Sheet. Work in well-ventilated areas and necessarily wear suitable personal protective equipment. For more information on the correct disposal, storage and handling of the product, please consult the relevant Safety Data Sheet. Work in well-ventilated areas and necessarily wear suitable personal protective equipment. For more information on the correct disposal, storage and handling of the product, please consult the relevant Safety Data Sheet.

APPLICATION SYSTEMS

reparation

New plasters with smooth or compact plaster finish, with regular texture:

Wait for the total seasoning; thorough brushing to remove inconsistencies; apply as a base coat of ALPHA BL GROND diluted at maximum 30% by volume with water or alternatively with IMPREGNANTE ALPHATEX SF diluted at 400% by volume with water, wait for it to dry completely; apply two coats of FONDO ALPHA EFFECTS MICRO or EXTRA diluted to 20 - 30% by volume with water depending on the application method adopted, waiting 4 - 6 hours between one coat and the next; in the case of roller application, the EXTRA version must be smoothed with a white plastic trowel; wait at least 12 hours after applying the last coat

Irregular gypsum plasters and skims never painted Even out the surfaces by smoothing them with ALPHA STUCCO or POLYFILLA PRO E200; wait for it to dry completely and sand to eliminate smudges and excess grout; apply a coat of ALPHA BL GROND diluted at maximum 30% by volume with water or alternatively with IMPREGNANTE ALPHATEX SF diluted at 400% by volume with water over the entire surface, wait for it to dry completely; apply two coats of FONDO ALPHA EFFECTS MICRO or EXTRA diluted to 20 - 30% by volume with water depending on the application method adopted, waiting 4 - 6 hours between one coat and the next; in the case of roller application, the EXTRA version must be smoothed with a white plastic trowel; wait at least 12 hours after applying the last coat

New plasterboard

Even out the surfaces by smoothing them with ALPHA STUCCO or POLYFILLA PRO E200; wait for it to dry completely and sand to eliminate smudges and excess grout; apply a coat of ALPHA BL GROND diluted at maximum 30% by volume with water or alternatively with IMPREGNANTE ALPHATEX SF diluted at 400% by volume with water over the entire surface, wait for it to dry completely; apply two coats of FONDO ALPHA EFFECTS MICRO or EXTRA diluted to 20 - 30% by volume with water depending on the application method adopted, waiting 4 - 6 hours between one coat and the next; in the case of roller application, the EXTRA version must be smoothed with a white plastic trowel; wait at least 12 hours after applying the last coat

Smooth substrates with well anchored old washable paints Fill any holes and irregularities with POLYFILLA PRO E200, F200 or F210; wait for it to dry completely and sand to eliminate smudges and excess grout; isolate the grouting with ALPHA BL GROND diluted up to 30% by volume with water or alternatively with ALPHATEX SF IMPREGNANTE diluted at 400% by volume with water, wait for it to dry completely; apply two coats of FONDO ALPHA EFFECTS MICRO or EXTRA diluted to 20 - 30% by volume with water depending on the application method adopted, waiting 4

- 6 hours between one coat and the other; in the case of roller application, the EXTRA version must be smoothed with a white plastic trowel; wait at least 12 hours after applying the last coat

Old tempera paintings

Removal of tempera paints by scraping them after having previously moistened them; isolate the surface with ALPHATEX SF IMPREGNANT diluted 400% by volume with water; wait 3 - 4 hours; even out the surfaces by smoothing them with ALPHA STUCCO or POLYFILLA PRO E200; wait for it to dry completely and sand to eliminate smudges and excess grout; apply a coat of ALPHA BL GROND diluted up to 30% by volume with water or alternatively with ALPHATEX SF IMPREGNANT diluted 400% by volume with water over the entire surface, wait for it to dry completely; apply two coats of FONDO ALPHA EFFECTS MICRO or EXTRA diluted to 20 - 30% by volume with water depending on the application method adopted, waiting 4 - 6 hours between one coat and the next; in the case of roller application, the EXTRA version must be smoothed with a white plastic trowel; wait at least 12 hours after applying the last coat

finishing

Apply one coat of ALPHA ELEGANCE with a short-haired wool roller and go over it, when still wet, with circular movements using a synthetic sponge; as an alternative to the sponge it is possible to use a fur glove or a synthetic cloth that does not release hair. To obtain the Armonie Bicolore effect, apply a second coat of ALPHA ELEGANCE in the same way after 4 - 6 hours from the application of the first coat.

- If you want to obtain the Iridescent Harmony effect, after applying the first coat of colored ALPHA ELEGANCE, it is necessary to apply one coat, with a short-haired wool roller, of ALPHA ELEGANCE MADREPERLA appropriately diluted.

Notes

All the information contained in this document is purely indicative and contains only some examples of support that do not represent the totality of the situations that in practice could be affected, therefore if it is necessary to intervene on supports not indicated or if further clarifications are necessary, we invite you to contact our Technical Assistance Service. Furthermore, for the correct preparation of the substrates and the application of the products, the rules for state-of-the-art installation apply, as reported in the Sikkens notebook "Preparation of masonry substrates", which we invite you to consult.

WORDING TO BE INCLUDED IN THE TENDER SPECIFICATIONS AND ESTIMATES

Semi-transparent water-based decorative finish for interiors, with a cloudy effect (ALPHA ELEGANCE type)

PHYSICAL CHARACTERISTICS

Viscosity:	Brookfield 1000 - 1500 cps at 20 ° C
Density (density):	1.00 ± 0.05 kg / dm ³
Ph:	7-9
Solid content:	28.5% by volume; 29.5% by weight

Drying at 23 ° C / 65% RH

Touch dry: 1 - 2 hours

Overcoating:

After 4 - 6 hours

Coloring:

Only with Akzo Nobel's Acomix tinting system using the N00 base. Also available in the ready mixed Mother of Pearl finish.

EU limit value for VOC content:

Cat. A / I: 200 g / l (2010). This product contains a maximum of 100 g / l of VOC

Physical values according to EN 13300

brilliance:	G3 Matt	≤ 10 OJ 85 °
dry film thickness:	E1	<50 µm
granulometry:	S1 End	<100 µm
wet abrasion:	Class 1	<5 µm after 200 cycles

The effectiveness of our products and systems is based on years of practical experience and research conducted in our laboratories. We guarantee that the quality of the work carried out with our products meets the eligibility requirements set by Akzo Nobel Coatings SpA, provided that all the instructions given by us are correctly followed and the work has been carried out according to skill and professionalism. In the event that the final result has been negatively influenced by circumstances beyond our control, any and all liability is expressly excluded and declined. The buyer is obliged to check whether the delivered products are suitable for the intended use.

We reserve the right to modify the content of this document without prior notice. As soon as a new version of this datasheet is available, it will no longer be valid.

relative Paints

NO)



based on years of practical experience and research conducted in our laboratories. We guarantee that the quality of the work carried out with our products, to Akzo Nobel Coatings SpA, provided that all instructions given by us are correctly followed and the work has been carried out as or where the final result has been adversely affected by circumstances beyond our control. our will, any and all responsibility is

Products delivered are suitable for the intended use. We reserve the right to modify the content of this document without prior notice. No technical data will be available, this will no longer be valid.