

FORM TECHNIQUE

VERONITE

(Cod. 353.101)

Matt base paint based on alkyd resins, with strong coverage and good expansion.
After 24 hours from application, it allows excellent sanding.
The product is suitably formulated for application on wooden supports and as a base coat for ferrous materials and mineral plasters. It can also be used as a matte finish.

CASATI
Veronte

CHARACTERISTICS:

APPEARANCE	Opalescent.
COMPOSITION	alkyd resins, titanium dioxide, fillers and various additives.
VISCOsITY FORD 8 20 ° C	20t2 sec.
RESISTANCE TO ALKALI	Good.
DRY RESIDUE	80t2%

SYSTEM APPLIED:

SUBSTRATE PREPARATION:

Sand the substrate before application; where there are dust, grease stains or patinas, remove them with mechanical action and suitable degreasing solvents.

DRYING

depending on the temperature, 1-3 hours dust-free, 12-18 hours in depth.

SURRENDER

10-12 m2 / the second of the substrate.

DILUTION

dilute with AQUARAGIA (code 320.001) or ODORLESS THINNER (code 330.001)
in

| EQUIP

reason of 5-10% maximum.

| STORAGE

product it can be applied by brush or roller.

In its original closed container and at a temperature between 5-40 degrees C.

AVAILABLE PACKAGES: 0.500 Liters; 2.5 Liters.

NOTES AND GENERAL WARNINGS

It is not recommended to apply VERONITE at temperatures below 5 ° C, above 35°C and with relative humidity > 70% in order to avoid drying delays and failure of the film to harden. SAFETY:

For information on the correct disposal, storage and handling of the product, please consult the relevant Safety Data Sheet.

All the technical indications contained herein are indicative. For further information, consult our Technical Assistance service.

Jan. 15; rev .: 02; Sbo / Am / g - ITA

