



AQUASAIL polished

Glossy water-based enamel

| | |
|---|--|
| Description | Water-based enamel for both indoor and outdoor applications, characterized by high hiding power and high resistance to atmospheric agents. |
| Composition | Based on aryl copolymers and pigments in aqueous solution |
| Specific weight medium | 1.130-1.190 kg / lt |
| Surrender | 15 - 18 sqm / l per coat |
| Percentage by weight of the dry resin on the total dry | 57% +/- 1 |
| Coverage | Great |
| Appearance of the film | Shiny |
| Resistance to wet abrasion | High |
| Resistance to weathering | High |
| Film thickness | 70 microns wet - 30 microns dry in both coats. |
| storage | In tightly closed package |
| Use | For the painting of surfaces both in iron and in wood, carefully treated. |
| Application | Brush, short-haired roller or spray |
| Dilution | Dilute with 5% -10% water. |
| Temperature of application | 10-35C ° relative humidity max. 85% |
| Drying at 25 ° C | Dry: 2 - 4 hours depending on the environmental conditions. |
| Over application | 6-8 hours |

Color White and colors GIOCKY Sistem

Pack of sale 0,375 lt - 0,750 lt - 2,5 lt

Cleaning tools Water and detergent

**Preparation
of the support**

NEW IRON:

- Leave the new iron to rust in the weather, so as to be able to eliminate the calamine present on the surface.
- Brush and completely eliminate the rust from the iron.
- Remove the grease and dirt using a NITRO THINNER.
- Apply two coats of AQUAPROT according to the instructions given in the technical data sheet.
- Apply two coats of AQUASAIL LUCIDO according to the instructions above.

ALREADY PAINTED IRON:

- Eliminate any inconsistencies in the substrate by carefully brushing and cleaning the substrate.
- Check the adhesion of the old paints, if necessary remove them with the help of a scraper, brush, sandblasting etc.
- Apply AQUAPROT on the parts where the iron is not covered.
- Apply two coats of AQUASAIL LUCIDO according to the instructions above.

NEW WOOD

- Carry out a thorough sanding of the substrate.
- Apply two coats of FONDO OPACO, according to the instructions above, sanding the surface between one coat and the other.
- Apply two coats of AQUASAIL LUCIDO according to the instructions above.

ALREADY PAINTED WOOD

- Eliminate any inconsistencies in the substrate with a thorough sanding and cleaning of the substrate And
- Apply two coats of FONDO OPACO, according to the instructions above, sanding the surface between one coat and the other.
- Apply two coats of AQUASAIL LUCIDO according to the instructions above.

ALUMINUM AND NEW GALVANIZED SHEET

- Sand and degrease the surface with DILUENTE NITRO Apply two
- coats of AQUASAIL LUCIDO according to the instructions above.

- **ALUMINUM AND GALVANIZED SHEET ALREADY PAINTED**
- Wash the surface with water and detergent using an abrasive sponge, in order to scratch the entire surface.
- Remove any old coats of paint that are not well adherent.
- Apply AQUAPROT in the presence of rust.
- Apply two coats of AQUASAIL LUCIDO according to the instructions above.

SPECIFICATION ITEM (for tenders and estimates)

| | |
|---|--|
| Description | Water-based enamel for both indoor and outdoor applications, characterized by high hiding power and high resistance to atmospheric agents. |
| Specific weight medium | 1.130-1.190 kg / lt |
| Percentage by weight of the dry resin on the total dry | 57% +/- 1 |

Warnings

- The substrate temperature must be at least 3C ° higher than the condensation temperature.
- Apply the product with temperatures ranging from 10C ° -35C ° and with a relative humidity of max. 85%
- If the product is applied in closed environments, continuous replacement is required air, so that the water vapors escape.
- Apply the product on a carefully treated surface.
- The yield may vary according to the characteristics of the substrate.
- Do not apply the product in direct sunlight.

The technical information contained in this sheet is the result of laboratory tests and practical experiences which do not involve any responsibility on our part, as the conditions of use are not under our direct control. In cases of doubt, it is always advisable to ask our technicians for further information regarding the correct application cycle.