



## SAIL

Alkyd enamel

---

<b>Description</b>	Glossy and matt alkyd enamel for exteriors and interiors.
<b>Composition</b>	Based on alkyl resins, with excellent resistance to light and atmospheric agents.
<b>Specific weight</b>	
medium	0,970 - 1,270 kg / lt depending on the color
Surrender	8 - 10 sqm / l per coat
<b>Percentage by weight of the dry resin on the total dry</b>	58% +/- 1
<b>Coverage</b>	Good
<b>Filling</b>	Good
<b>Appearance of the film</b>	Glossy or matte
<b>Resistance to weathering</b>	Good
<b>Film thickness</b>	25 - 30 microns per coat
<b>storage</b>	In tightly closed package
<b>Use</b>	For the painting of surfaces both in iron and in wood, carefully treated.
<b>Application</b>	Brush or roller
<b>Dilution</b>	5% by volume with synthetic thinner
<b>Temperature of application</b>	10-35C ° relative humidity max. 85%
<b>Drying</b>	
at 25 ° C	Dry: 6 - 8 hours Hardened: 18 - 24 hours
<b>Over application</b>	24 hours
<b>Color</b>	White and folder colors

**Pack of sale** 0,125 lt - 0,375 lt - 0,750 lt - 2,5 lt

**Cleaning tools** Synthetic thinner

---

**Preparation of the support**

**NEW IRON:**

- Leave the new iron to rust in the weather, so as to be able to eliminate the calamine present on the surface.
- Brush and completely eliminate the rust from the iron.
- Remove the grease and dirt using a NITRO THINNER.
- Apply two coats of PROTEFER ZINCO according to the instructions given in the technical data sheet.
- Apply two coats of SAIL according to the instructions above.

**ALREADY PAINTED IRON:**

- Eliminate any inconsistencies in the substrate by carefully brushing and cleaning the substrate.
- Check the adhesion of the old paints, if necessary remove them with the help of a scraper, brush, sandblasting etc.
- Apply PROTEFER ZINC on the parts where the iron is not covered.
- Apply two coats of SAIL according to the instructions above.

**NEW WOOD**

- Carry out a thorough sanding of the substrate.
- Apply two coats of CEMENTOL, according to the instructions above, sanding the surface between one coat and the next.
- Apply two coats of SAIL according to the instructions above.

**ALREADY PAINTED WOOD**

- Eliminate any inconsistencies in the substrate with a thorough sanding and cleaning of the substrate And
- Apply two coats of CEMENTOL, according to the instructions above, sanding the surface between one coat and the next.
- Apply two coats of SAIL according to the instructions above.

---

**SPECIFICATION ITEM (for tenders and estimates)**

**Description** Glossy and matt alkyd enamel for exteriors and interiors.

**Specific weight**  
medium 0,970 - 1,270 kg / lt depending on the color

**Percentage by weight of the dry resin on the total dry** 58% +/- 1

---

## Warnings

- The substrate temperature must be at least 3C ° higher than the condensation temperature.
- Apply the product with temperatures ranging from 10C ° -35C ° and with a relative humidity of max. 85%
- If the product is applied indoors, a continuous air exchange is required, so that the water vapors escape.
- Apply the product on a carefully treated surface.
- The yield may vary according to the characteristics of the substrate.
- Do not apply the product in direct sunlight.

The technical information contained in this sheet is the result of laboratory tests and practical experiences which do not involve any responsibility on our part, as the conditions of use are not under our direct control. In cases of doubt, it is always advisable to ask our technicians for further information regarding the correct application cycle.