



STARQUARZ

Quartz flour acrylic coating

Description	Acrylic coating for exteriors and interiors characterized by excellent resistance to atmospheric agents. The product has a good filling and masking power.	
Composition	Based on acrylic resins, quartz flour and pigments and selected in aqueous dispersion.	
Specific weight medium	1,500 - 1540 kg / lt	
Surrender	Smooth finishes	8 - 10 sqm / l per coat
	Peeled finishes	3 - 4 sqm / l per coat
Percentage by weight of the dry resin on the total dry	12.5% +/- 1	
Coverage	Great	
Filling	Optimal	
Appearance of the film	Opaque	
Resistance to weathering	<p>The product completes the polymerization and drying process in 10 or 15 days in optimal environmental conditions (5-30 ° C; RH max. 85%).</p> <p>Should the product occur in this period of time rainy events, unsightly drippings with a translucent and sticky appearance could be highlighted. This phenomenon is temporary, which does not affect the resistance of the product and can be easily eliminated by washing or waiting subsequent rainy events</p>	
Resistance on the outside	Excellent in light and atmospheric agents.	
storage	In tightly closed package	
Use	Plaster and masonry	
Application	Brush and roller	

Dilution	Smooth finishes Peeled finishes	25% - 40% by volume with water 1st coat 25% by volume with water 2nd coat 0 - 10% by volume with water
Temperature of application	10-35C ° relative humidity max. 85%	
Drying at 25 ° C	4 - 6 hours	
Over application	6 - 8 hours	
Color	White and colors GIOCKY Sistem	
Pack of sale	0,750 lt - 4 lt - 14 lt	
Cleaning tools	Water and detergent	

Preparation of the support

NEW WALL

- Brush to remove any inconsistencies on the substrate.
- Apply a coat of DYON 46 acrylic insulation diluted 1: 6 with water.
- Apply two coats of STARQUARZ according to the instructions above.

ON ALREADY PAINTED WALL

- Eliminate any inconsistencies in the substrate by carefully brushing and cleaning the substrate.
- Check the adhesion of the old paints, if necessary remove them with a wet sponge, scraper, brushing, sandblasting etc.
- Apply a coat of undiluted PROFIX solvent-based insulation.
- Apply two coats of STARQUARZ according to the instructions above.

NB.

On new plaster it is advisable to wait at least 30 days for the application of STARQUARZ in order to allow complete curing of the substrate.

On crumbling plaster, it is advisable to apply a coat of undiluted PROFIX solvent-based insulation.

SPECIFICATION ITEM (for tenders and estimates)

Description Acrylic coating for exteriors and interiors characterized by excellent resistance to atmospheric agents. The product has a good filling and masking power.

Specific weight
medium 1,500 - 1540 kg / lt

**Percentage by weight
of the dry resin
on the total dry** 12.5% +/- 1

Warnings

- The substrate temperature must be at least 3C ° higher than the condensation temperature.
- Apply the product with temperatures ranging from 10C ° -35C ° and with a relative humidity of max. 85%
- If the product is applied indoors, a continuous air exchange is required, so that the water vapors escape.
- Apply the product on a carefully treated surface.
- The yield may vary according to the characteristics of the substrate.
- Do not apply the product in direct sunlight.

The technical information contained in this sheet is the result of laboratory tests and practical experiences which do not involve any responsibility on our part, as the conditions of use are not under our direct control. In cases of doubt, it is always advisable to ask our technicians for further information regarding the correct application cycle.